

### Step 1: Basic Cleaning



Finalit No. 5 Coating Remover for existing coatings



Use No. 5 undiluted and agitate immediately




Rinse with water after approx. 15 minutes

No. 5: 1l for up to 20 m<sup>2</sup>, depending on the degree of soiling

Finalit No. 9 Lime and Cement Bloom Remover + Finalit No. 1 Intensive Cleaner (Neutralisation)



Dilute No. 9 up to a ratio of 1:10 with water



Apply No. 9 and agitate immediately



After approx. 15 min. re-agitate if necessary. Then rinse thoroughly




Dilute No. 1 in a ratio of 1:20 with water



Apply No. 1 and agitate immediately



Rinse with water after approx. 15 minutes




Allow cleaned surface to dry

No. 9: 1l for up to 30 m<sup>2</sup>, depending on the degree of soiling  
No. 1: 1l for up to 60 m<sup>2</sup>

### Step 2: Protection



Finalit No. 21S Pores Filler + Finalit No. 25 Premium-Cool Impregnation




Dilute No. 21S up to a ratio of max. 1:3 with water




Apply 1-2 times, depending on the absorbency



Remove excess product immediately, let dry




Pour No. 25 into container and use undiluted



Apply 1-2 times, depending on the absorbency



Remove excess product immediately



Long term protection

No. 21S: 1l for up to 30m<sup>2</sup>, depending on the absorbency of the material  
No. 25: 1l for up to 80m<sup>2</sup>, depending on the absorbency of the material

1  
Basic Cleaning

2  
Protection